

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
15 May 2003 (15.05.2003)

PCT

(10) International Publication Number  
**WO 03/039743 A1**

(51) International Patent Classification<sup>7</sup>: **B01J 23/648**,  
23/656, 23/63, 23/652, 23/89, C07C 209/36

(21) International Application Number: PCT/EP02/09874

(22) International Filing Date:  
4 September 2002 (04.09.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
101 54 811.7 8 November 2001 (08.11.2001) DE  
60/333,153 27 November 2001 (27.11.2001) US  
102 16 108.9 12 April 2002 (12.04.2002) DE

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant: **DEGUSSA AG** [DE/DE]; Bennigsenplatz 1, 40474 Düsseldorf (DE).

(72) Inventors: **KRAUTER, Jürgen**; Eisenbahnstrasse 206, 63303 Dreieich (DE). **GROSS, Michael**; Rossdorfer Strasse 33, 60385 Frankfurt/Main (DE). **PACKRUHN, Uwe**; Atzelbergstrasse 35, 60389 Frankfurt/Main (DE). **GÖTTLINGER, Markus**; Barbarossastrasse 19, 63517 Rodenbach (DE).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: SUPPORTED CATALYST FOR HYDROGENATION OF NITROAROMATICS

(57) Abstract: Supported, hydrogenating catalyst in powder form containing, as a catalytically active component, a primary precious metal component, a secondary precious metal component and one or more non-precious metal components. It is used for the hydrogenation of nitroaromatics, in particular nitrobenzene and DNT.

WO 03/039743 A1

## SUPPORTED CATALYST FOR HYDROGENATION OF NITROAROMATICS

The invention relates to a supported hydrogenating catalyst in powder form, a process for its production and its use in the catalytic hydrogenation of nitroaromatics.

The hydrogenation of aromatic nitro-compounds to amines is one of the major ways of producing amines in industrial chemistry. Today, aromatic amines are central components in the production of fine, speciality and even bulk chemicals. Examples in the field of bulk chemicals, in particular, are aniline and toluenediamines (TDA). The catalytic hydrogenation of nitrobenzene to aniline replaced the old Bechamps reduction method, making an important contribution to sustained development. TDA can be regarded as an intermediate for the production of polyurethane foams, being converted in a phosgenation reaction to toluene diisocyanate (TDI), which is processed together with polyalcohols to produce polyurethane foams.

Various processes and catalysts are known for the production of aromatic amines by hydrogenation of the corresponding aromatic nitro-compounds. In addition to the hydrogenation of nitrobenzene to aniline in the gas phase, there are a number of other processes, all of which work in the liquid phase. In addition to supported non-precious metal catalysts and Raney-type catalysts, supported catalysts containing precious metals are also used.

A number of catalysts are known for the catalytic hydrogenation of nitroaromatics, in particular of dinitrotoluene, in the suspension phase.

US 2,823,235 discloses palladium, platinum and palladium-platinum catalysts on black, which are doped with iron.

Very similar catalysts, which contain blacks as supports, are disclosed in US 3,127,356.

US 4,256,671 discloses, in addition to Pd and Pt, also Ni, Ru and Rh as a precious metal component for catalysts used  
5 in the catalytic hydrogenation of dinitrotoluenes to toluediamines.

US 6,096,924 discloses, as a catalytically active component, Rh, Ru, Ir, Pt, Pd, Ni and Co. These metals are applied to powder-form supports. V is used as a doping  
10 metal.

DE 199 11 865 A1 discloses a similar system with Ir as the precious metal and V as the doping metal.

Whilst the stated printed publications disclose Pd-, Ir- or Pd-Pt-catalysts, US 4212824 discloses a Pt-catalyst on  
15 black, which is doped with Fe. Fe and V are the non-precious metals used by far the most frequently for doping.

It is also known that the addition of a few mol-percent of platinum (for example 15 mol%) to supported palladium catalysts produces a positive synergetic effect on  
20 activity. This is disclosed in *Pol. Chem. Stosow.* 1981, 25(1), 53-68 or in *Chin. Chem. Lett.* 1996, 7(7), 663-664.

The former printed publication shows that platinum may be present only in a smaller molar quantity than palladium. The optimum is ca. 20 mol% Pt in relation to Pd. If a  
25 larger quantity of Pt is used, lower activity is determined.

The object of the present invention is to improve the selectivity and activity of the catalytic hydrogenation of nitroaromatics to aminoaromatics, i.e. to reduce the  
30 formation of by-products and to increase the yield of the desired product, through the selection and production of a hydrogenating catalyst.

## 3

The invention provides a supported hydrogenating catalyst in powder form, which contains, as catalytically active components, a mixture of a primary precious metal component, a secondary precious metal component and one or more non-precious metal components, wherein either Pt is used as the primary precious metal component with Pd, Ru, Rh as the secondary precious metal component and V, Fe, Mn, Ce and/or Cr as the non-precious metal component, or Pd is used as the primary precious metal component with Ru, Rh as the secondary precious metal component and V, Fe, Mn, Ce and/or Cr as the non-precious metal component or Pd is used as the primary precious metal component with Pt as the secondary precious metal component and Ce and/or Cr as the non-precious metal component.

The hydrogenating catalyst according to the invention can contain, per 100 g dry hydrogenating catalyst, 10 to 50 mmol of the primary precious metal component. The proportion of the secondary precious metal component can be 1 to 60 mol% in relation to the primary precious metal component, preferably 8 to 12 mol% in relation to the primary precious metal component and that of the non-precious metal component 1-700 mol%, preferably 100-600 mol% in relation to the primary precious metal component.

The formation of by-products is influenced only slightly by the ratio of primary to secondary precious metal components which, however has a strong influence on the activity of the catalyst.

As doping metals for the combination Pt as primary precious metal component and Pd, Ru, Rh as secondary precious metal component, V, Fe, Mn, Ce and/or Cr are particularly suitable as the non-precious metal component.

As doping metals for the combination Pd as primary precious metal component and Ru, Rh as secondary precious metal component, V, Fe, Mn, Ce and/or Cr are particularly suitable as the non-precious metal component.

As a doping metal for the combination Pd as primary precious metal component and Pt as secondary precious metal component, Ce and/or Cr are particularly suitable as the non-precious metal component.

- 5 Whilst the secondary precious metal component is responsible for the high activity of the catalyst, the non-precious metal component is decisive for selectivity.

The hydrogenating catalyst according to the invention can contain, per 100 g dry hydrogenating catalyst, 15 to 20  
10 mmol of the primary precious metal component, 8 to 12 mol%, in relation to the primary precious metal component, of the secondary precious metal component, and 1 to 600 mol%, in relation to the primary precious metal component, of cerium.

- 15 Supports in powder form are used as supports, and these powder supports may be physically activated carbons, chemically activated carbons, blacks, aluminium oxides or silicon oxides, preferably physically activated carbons, chemically activated carbons or blacks.

- 20 The invention further provides a process for the production of the hydrogenating catalyst according to the invention, which is characterised in that an aqueous solution containing the primary and secondary precious metal components and the non-precious metal component in  
25 dissolved form is added to a suspension of a powder-form support material in water, the primary and secondary precious metal components and the non-precious metal component are deposited on the powder-form support using a base and reduction is optionally carried out using a  
30 reducing agent such as for example formaldehyde, hydrazine, hydrogen, sodium tetrahydroborate, formic acid or sodium formate.

Reduction can be carried out at a temperature of 0 to 100°C.

## 5

- The order in which the support material, water, metal salt solutions and reducing agents are added can also be varied. Optionally, reduction can take place with hydrogen on the dried catalyst. The use of a reducing agent is optional,
- 5 i.e. the catalyst according to the invention can be separated out from the reaction mixture by filtration, without the addition of a reducing agent, after the primary and secondary precious metal and non-precious metal components have been deposited on the support.
- 10 The catalyst according to the invention can be used for the hydrogenation of nitroaromatics. The catalyst according to the invention can be used in particular for the hydrogenation of nitrobenzene to aniline and for the hydrogenation of dinitrotoluenes to toluenediamines.
- 15 The catalytic hydrogenation of the nitro-compound can be carried out in the liquid phase as a continuously or discontinuously operated process at pressures of 1 to 100 bar and temperatures of 0 to 250°C in the presence of the catalyst according to the invention.
- 20 The catalytic hydrogenation of the nitro-compound in the liquid phase can be carried out as a continuously or discontinuously operated process at pressures of 1 to 100 bar and temperatures of 0°C to 200°C in the presence of the catalyst according to the invention.
- 25 The catalytic hydrogenation of nitrobenzene or dinitrotoluenes in the presence of the catalyst according to the invention can be carried out in a continuously or discontinuously operated agitated reactor or in a continuously operated circulating reactor in the presence
- 30 of a solvent, such as for example methanol or toluene. The solvent can also be a mixture of aniline and water, for the hydrogenation of nitrobenzene, or a mixture of dinitrotoluenes in water, for the hydrogenation of dinitrotoluenes.

The hydrogenation of dinitrotoluenes to toluediamines can be carried out at temperatures of 70 to 200°C, preferably 90 to 150°C, and pressures of 1 to 100 bar, preferably 10 to 40 bar. If hydrogenation is carried out continuously, the quantity of converted dinitrotoluenes must be replaced by topping up and the product-water mixture must be removed from the reactor.

When using the catalyst according to the invention, a synergetic effect is observed i.e. the addition of the secondary precious metal component increases the activity of the catalyst significantly in comparison with the corresponding catalyst containing no second precious metal.

This could not be expected from the prior art according to the printed publications *Pol. Chem. Stosow.* 1981, 25(1), 53-68 or *Chin. Chem. Lett.* 1996, 7(7), 663-664, as they disclose that the activity of the Pd falls if the proportion of Pt is increased.

Consequently, it is surprising that Pd as a secondary precious metal component has a similar synergetic effect when Pt is used as the primary precious metal component.

There is no reference at all in the literature to particularly high activity of the other metal combinations in the hydrogenation of nitro groups. On the contrary, the use of Rh or Ru as a secondary precious metal component would have been expected to have a negative effect as it is known (see for example P. N. Rylander, *Catalytic Hydrogenation in Organic Syntheses*, Academic Press, 1979, New York, page 175 ff), that Rh and Ru are highly suitable for hydrogenating aromatic rings and would thus be likely to have poor selectivity (i.e. undesirable secondary reactions). Surprisingly, this is not observed.

Examples

Catalysts according to the invention and reference catalysts are produced and their catalytic properties in the hydrogenation of nitroaromatics are compared.

5

Reference example 1: Pd-containing trimetallic catalyst on black

Production of a Pd-Pt-Fe/SB trimetallic catalyst (1.6% Pd + 0.2% Pt + 4.0% Fe) with Pd as the primary precious metal component, Pt as the secondary precious metal component and a non-precious metal component according to the prior art. The product Shawinigan Black from Chevron (abbreviated in the catalyst to SB = Shawinigan Black) is used as the black support. The Pd-Pt-Fe/SB (1.6% Pd, 0.2% Pt, 4.0% Fe) catalyst is produced as disclosed in US 3,127,356, Example VII.

Example 1: Trimetallic catalyst on black

22.06 g Shawinigan Black (commercial product of Chevron, abbreviated in the catalyst to SB = Shawinigan Black) are suspended in 2000 ml de-ionised water and the suspension is set at a pH of 10 using sodium carbonate solution. A solution of 2 g tetrachloropalladic(II)acid (20%), 0.2 g hexachloroplatinic(IV)acid (25%) and 6.98 g cerium(III)chloride heptahydrate in 200 ml deionised water is added to this suspension. After heating to 80°C the pH is set at 6.4 using sodium carbonate solution, and the suspension is stirred and filtered. 100 g dry catalyst contains 1.6% Pd, 0.2% Pt and 10.5% Ce. The catalyst is abbreviated to Pd-Pt-Ce/SB (1.6, 0.2, 10.5).



## 8

Reference example 2: Bimetallic catalyst on black

The catalyst Pd-Pt/SB (1.6% Pd, 0.2% Pt) is produced as described in example 1, but instead of the quantities given there, 24.69 g Shawinigan Black is used and no cerium salt.

5 100 g dry catalyst contains 1.6% Pd and 0.2% Pt.

Reference example 3: Pd-containing trimetallic catalyst on activated carbon

98.21 g activated carbon are suspended in 500 ml de-ionised  
10 water and the suspension is set at a pH of 10 using sodium carbonate solution. 8 g tetrachloropalladic(II) acid (20%), 0.8 g hexachloroplatinic(IV) acid (25%) and 30.39 g iron(III)nitrate-nonahydrate, dissolved in 200 ml de-ionised water are added to this suspension. After heating  
15 to 80°C, the pH is set at 6.4 using sodium carbonate solution and the suspension is stirred, reduced with formaldehyde and filtered. 100 g dry catalyst contains 1.6% Pd, 0.2% Pt and 4.2% Fe. The catalyst is abbreviated to Pd-Pt-Fe/AC (1.6, 0.2, 4.2).

**Example 2:** Pd-containing trimetallic catalysts on activated carbon

Activated carbon is suspended in 500 ml de-ionised water and the suspension is set at a pH of 10 using sodium carbonate solution. 8 g tetrachloropalladic(II) acid (20%), a solution of the secondary precious metal component and a salt of the non-precious metal component, dissolved in 200 ml de-ionised water are added to this suspension. After heating to 80°C the pH is set at 6.4 using sodium carbonate solution and the suspension is stirred, reduced with formaldehyde and filtered. The quantities are given in Table 1.

**Example 3:** Pt-containing trimetallic catalysts on activated carbon

Activated carbon is suspended in 500 ml de-ionised water and the suspension is set at a pH of 10 using sodium carbonate solution. 11.6 g hexachloroplatinic(IV) acid (25%), a solution of the secondary precious metal component and a salt of the non-precious metal component, each dissolved in 200 ml de-ionised water, are added to this suspension. After heating to 80°C, the pH is set at 6.4 with sodium carbonate solution, and the suspension is stirred, reduced with formaldehyde and filtered. The quantities are given in Table 2.

Table 1. Data for Example 2.

Catalyst	Composition	Quantity of activated carbon	Solution of secondary precious metal component	Salt of non-precious metal component
Pd-Ru-Fe/AC	1.6, 0.1, 4.2	98.31 g	RuCl <sub>3</sub> (20%) 0.49 g	Fe(NO <sub>3</sub> ) <sub>3</sub> (H <sub>2</sub> O) <sub>9</sub> 30.39 g
Pd-Rh-Fe/AC	1.6, 0.1, 4.2	98.31 g	RhCl <sub>3</sub> (20%) 0.5 g	Fe(NO <sub>3</sub> ) <sub>3</sub> (H <sub>2</sub> O) <sub>9</sub> 30.39 g
Pd-Pt-Ce/AC	1.6, 0.2, 10.5	91.63 g	H <sub>2</sub> PtCl <sub>6</sub> (25%) 0.8 g	CeCl <sub>3</sub> (H <sub>2</sub> O) <sub>7</sub> 27.93 g
Pd-Ru-Ce/AC	1.6, 0.1, 10.5	91.98 g	RuCl <sub>3</sub> (20%) 0.49 g	CeCl <sub>3</sub> (H <sub>2</sub> O) <sub>7</sub> 27.93 g
Pd-Rh-Ce/AC	1.6, 0.1, 10.5	91.98 g	RhCl <sub>3</sub> (20%) 0.5 g	CeCl <sub>3</sub> (H <sub>2</sub> O) <sub>7</sub> 27.93 g

Table 2. Data for Example 3.

Catalyst	Composition	Quantity of activated carbon	Solution of secondary precious metal component	Salt of non-precious metal component
Pt-Ru-Fe/AC	2.9, 0.1, 4.2	96.95 g	RuCl <sub>3</sub> (20%) 0.49 g	Fe(NO <sub>3</sub> ) <sub>3</sub> (H <sub>2</sub> O) <sub>9</sub> 30.39 g
Pt-Rh-Fe/AC	2.9, 0.1, 4.2	96.95 g	RhCl <sub>3</sub> (20%) 0.5 g	Fe(NO <sub>3</sub> ) <sub>3</sub> (H <sub>2</sub> O) <sub>9</sub> 30.39 g
Pt-Pd-Fe/AC	2.9, 0.1, 4.2	96.95 g	H <sub>2</sub> PdCl <sub>4</sub> (20%) 0.5 g	Fe(NO <sub>3</sub> ) <sub>3</sub> (H <sub>2</sub> O) <sub>9</sub> 30.39 g
Pt-Ru-Ce/AC	2.9, 0.1, 10.5	90.62 g	RuCl <sub>3</sub> (20%) 0.49 g	CeCl <sub>3</sub> (H <sub>2</sub> O) <sub>7</sub> 27.93 g
Pt-Rh-Ce/AC	2.9, 0.1, 10.5	90.62 g	RhCl <sub>3</sub> (20%) 0.5 g	CeCl <sub>3</sub> (H <sub>2</sub> O) <sub>7</sub> 27.93 g
Pt-Pd-Ce/AC	2.9, 0.2, 10.5	90.62 g	H <sub>2</sub> PdCl <sub>4</sub> (20%) 0.5 g	CeCl <sub>3</sub> (H <sub>2</sub> O) <sub>7</sub> 27.93 g

## 12

The catalysts according to the examples are used in the discontinuous hydrogenation of dinitrotoluene to toluenediamine and the activity and selectivity of the catalysts are determined.

5 The reaction is carried out in a 0.5 l Hastelloy autoclave. First, 40 g 2,4-Dinitrotoluene, 101 g 2,4-toluenediamine, 59 g water and 1.2 g catalyst (in relation to the solids) are fed into the autoclave. Then, after locking the autoclave, the gas space is flushed first with nitrogen and  
10 then with hydrogen and finally a hydrogen pressure of 10 bar is established.

After heating to 120°C, the reaction is started by switching on the stirring mechanism. The end point of the reaction can be determined precisely by the rapid reduction  
15 in hydrogen absorption.

Hydrogen absorption is recorded during the reaction. Once the reaction has ended and the reaction mixture has cooled, it is taken up in methanol, filtered and analysed by gas chromatography. This allows the yield of TDA, the  
20 conversion of DNT and the quantity of by-products to be determined.

The following can be obtained as by-products: toluidines, diaminobenzenes (called low-boilers) and tars. The term tars describes all compounds which have a longer retention  
25 time than the primary product TDA.

Activity is calculated from the absorption of hydrogen during the reaction time in relation to the catalyst mass and is given as ml H<sub>2</sub>/(min g catalyst). The results are summarised in Table 3, Table 4 and Table 5.

## Tables of results

Table 3. Pd-containing catalysts on black

	Catalyst	Charge	Activity [ml H <sub>2</sub> /min g]	Low boilers [%]	TDA yield [%]	Tars [%]
Reference example 1	Pd-Pt-Fe/SB	1.6, 0.2, 4.2	1000	0.01	97.92	2.07
Reference example 2	Pd-Pt/SB	1.6, 0.2	1050	0.28	98.85	0.87
Example 1	Pd-Pt-Ce/SB	1.6, 0.2, 10.5	1200	0.0	99.47	0.53

Table 4. Pd-containing trimetallic catalysts on activated carbon

	Catalyst	Charge	Activity [ml H <sub>2</sub> /min g]	Low-boilers [%]	TDA yield [%]	Tars [%]
Reference example 3	Pd-Pt-Fe/AC	1.6, 0.2, 4.2	917	0.01	97.98	2.01
Example 2	Pd-Ru-Fe/AC	1.6, 0.1, 4.2	913	0.01	97.8	2.19
Example 2	Pd-Rh-Fe/AC	1.6, 0.1, 4.2	901	0.01	98.28	1.71
Example 2	Pd-Pt-Ce/AC	1.6, 0.2, 10.5	866	0.01	99.58	0.41
Example 2	Pd-Ru-Ce/AC	1.6, 0.1, 10.5	777	0.01	99.64	0.35
Example 2	Pd-Rh-Ce/AC	1.6, 0.1, 10.5	800	0.02	99.64	0.34

Table 5. Pt-containing trimetallic catalysts on activated carbon

	Catalyst	Charge	Activity [ml H <sub>2</sub> /min g]	Low-boilers [%]	TDA yield [%]	Tars [%]
Reference example 3	Pd-Pt-Fe/AC	1.6, 0.2, 4.2	917	0.01	97.98	2.01
Example 3	Pt-Ru-Fe/AC	2.9, 0.1, 4.2	923	0.01	99.38	0.61
Example 3	Pt-Rh-Fe/AC	2.9, 0.1, 4.2	920	0.00	99.13	0.87
Example 3	Pt-Pd-Fe/AC	2.9, 0.1, 4.2	950	0.01	99.2	0.79
Example 3	Pt-Ru-Ce/AC	2.9, 0.1, 10.5	895	0.05	99.61	0.39
Example 3	Pt-Rh-Ce/AC	2.9, 0.1, 10.5				
Example 3	Pt-Pd-Ce/AC	2.9, 0.2, 10.5	892	0.08	99.35	0.57



## Claims

1. Supported hydrogenating catalyst in powder form containing, as catalytically active components, a mixture of a primary precious metal component, a  
5 secondary precious metal component and one or more non-precious metal components, wherein either Pt can be used as the primary precious metal component with Pd, Ru, Rh as the secondary precious metal component and V, Fe, Mn, Ce and/or Cr as the non-precious metal  
10 component, or Pd can be used as the primary precious metal component with Ru, Rh as the secondary precious metal component and V, Fe, Mn, Ce and/or Cr as the non-precious metal component or Pd can be used as the primary precious metal component with Pt as the  
15 secondary precious metal component and Ce and/or Cr as the non-precious metal component.
2. Supported hydrogenating catalyst in powder form according to claim 1, characterised in that physically activated carbons, chemically activated carbons,  
20 blacks, aluminium oxides or silicon oxides are used as the powder-form support.
3. Hydrogenating catalyst according to claim 1, characterised in that 100 g dry hydrogenation catalyst contains 10-50 mmol of the primary precious metal  
25 component, 1-60 mol%, in relation to the primary precious metal component, of the secondary precious metal component, and 1-700 mol%, in relation to the primary precious metal component, of the non-precious metal component.
- 30 4. Hydrogenating catalyst according to claim 1, characterised in that 100 g dry hydrogenating catalyst contains 15-20 mmol of the primary precious metal component, 8-12 mol%, in relation to the primary precious metal component, of the secondary precious

metal component and 1-600 mol%, in relation to the primary precious metal component, of cerium.

- 5 5. Process for the production of a hydrogenating catalyst according to claims 1-4, characterised in that an aqueous solution containing the primary precious metal component, the secondary precious metal component and the non-precious metal component in dissolved form is added to a suspension of a powder-form support in water, the primary and secondary precious metal components and the non-precious metal component are deposited on the powder-form support material using a base and reduction is optionally carried out using a reducing agent.
- 10 6. Use of the catalyst according to claims 1-4 for the hydrogenation of nitroaromatics to aminoaromatics.
- 15 7. Use of the catalyst according to claims 1-4 for the hydrogenation of nitrobenzene to aniline.
8. Use of the catalyst according to claims 1-4 for the hydrogenation of dinitrotoluenes to toluenediamines.
- 20 9. Process for the production of aniline, characterised in that the catalytic hydrogenation of the corresponding nitro-compound is carried out in the liquid phase as a continuously or discontinuously operated process at pressures of 1 to 100 bar and temperatures of 0°C to 200°C in the presence of the catalyst according to claims 1-4.
- 25 10. Process for the production of toluenediamines, characterised in that the catalytic hydrogenation of the corresponding nitro-compounds is carried out in the liquid phase as a continuously or discontinuously operated process at pressures of 1 to 100 bar and temperatures of 0°C to 200°C in the presence of the catalyst according to claims 1-4.
- 30

# INTERNATIONAL SEARCH REPORT

Internat application No  
PCT/EP 02/09874

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J23/648 B01J23/656 B01J23/63 B01J23/652 B01J23/89  
C07C209/36

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, API Data, COMPENDEX, INSPEC

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 127 356 A (HAMILTON JR JEFFERSON MERRIT ET AL) 31 March 1964 (1964-03-31) cited in the application column 2, line 53 - line 57; examples II, V, VII	1, 2, 5-10
X	EP 0 994 520 A (DEGUSSA) 19 April 2000 (2000-04-19) abstract; claims 1-6; example 1	1-3, 5
A	YANG ET AL.: "Synergic effect of polymer supported Pd-Pt bimetallic catalysts on the hydrogenation of nitroaromatics" CHIN. CHEM. LET., vol. 7, no. 7, 1996, pages 663-664, XP008012980 cited in the application the whole document	1-10
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

24 March 2003

Date of mailing of the international search report

02 04 2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Veefkind, V

## INTERNATIONAL SEARCH REPORT

Internat Application No  
PCT/EP 02/09874

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 616 806 A (NAGATA TERUYUKI ET AL) 1 April 1997 (1997-04-01) claims 1,3; example I ---	1,2
X	US 6 111 140 A (BUYSCH HANS-JOSEF ET AL) 29 August 2000 (2000-08-29) column 3, line 7 - line 21 column 4, line 27 - line 31; examples 5,9-12 ---	1-5
X	EP 1 033 361 A (BASF AG) 6 September 2000 (2000-09-06) abstract paragraph '0043! - paragraph '0046! ---	1,6-10
X	GB 2 112 414 A (METALLURG IM A A BAIKOVA AKADE; NEFTEKHIMICHESKOGO SINTEZA IM) 20 July 1983 (1983-07-20) page 2, line 37 - line 45; claims 1,2; table 5 ---	1,6-8
X	US 5 993 762 A (RAJARAM RAJ R ET AL) 30 November 1999 (1999-11-30) table 7 ---	1
X	US 4 426 319 A (BLANCHARD GILBERT ET AL) 17 January 1984 (1984-01-17) examples 1-12 -----	1

# INTERNATIONAL SEARCH REPORT

Int'l application No.  
PCT/EP 02/09874

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

**FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210**

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

**1. Claims: 1-10 (in part)**

Claims 1-10, insofar relating to a catalyst containing Pt as primary precious metal component with Pd, Ru, Rh as second precious metal component and V, Fe, Mn, Ce and/or Cr as non-precious metal component.

**2. Claims: 1-10 (in part)**

Claims 1-10, insofar relating to a catalyst containing Pd as primary precious metal component with Ru, Rh as second precious metal component and V, Fe, Mn, Ce and/or Cr as non-precious metal component.

**3. Claims: 1-10 (in part)**

Claims 1-10, insofar relating to a catalyst containing Pd as primary precious metal component with Pt as second precious metal component and Ce and/or Cr as non-precious metal component.

# INTERNATIONAL SEARCH REPORT

ation on patent family members

Intern

Application No

PCT/EP 02/09874

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3127356	A	31-03-1964	NONE	
EP 0994520	A	19-04-2000	DE 19848032 A1 BR 9904688 A EP 0994520 A1 JP 2000123843 A US 6165635 A	20-04-2000 08-08-2000 19-04-2000 28-04-2000 26-12-2000
US 5616806	A	01-04-1997	JP 2801381 B2 JP 4128254 A BR 9103981 A DE 69110590 D1 DE 69110590 T2 EP 0476404 A2 HU 61520 A2 KR 9408912 B1	21-09-1998 28-04-1992 26-05-1992 27-07-1995 11-01-1996 25-03-1992 28-01-1993 28-09-1994
US 6111140	A	29-08-2000	DE 19641688 A1 AU 4557797 A CZ 9901247 A3 WO 9815351 A1 EP 0946293 A1 JP 2001501531 T	16-04-1998 05-05-1998 15-12-1999 16-04-1998 06-10-1999 06-02-2001
EP 1033361	A	06-09-2000	DE 19909168 A1 CN 1269353 A DE 50000852 D1 EP 1033361 A1 JP 2000256279 A US 6140539 A	07-09-2000 11-10-2000 16-01-2003 06-09-2000 19-09-2000 31-10-2000
GB 2112414	A	20-07-1983	NONE	
US 5993762	A	30-11-1999	AT 192668 T AU 675463 B2 AU 5247493 A CA 2111529 A1 DE 69328610 D1 DE 69328610 T2 DK 602865 T3 EP 0602865 A1 ES 2145036 T3 GR 3033466 T3 JP 6219721 A PT 602865 T US 5480854 A	15-05-2000 06-02-1997 30-06-1994 19-06-1994 15-06-2000 11-01-2001 07-08-2000 22-06-1994 01-07-2000 29-09-2000 09-08-1994 31-08-2000 02-01-1996
US 4426319	A	17-01-1984	FR 2501065 A1 AU 548741 B2 AU 8110582 A DE 3260185 D1 EP 0060740 A1 JP 57159544 A JP 61003531 B	10-09-1982 02-01-1986 16-09-1982 05-07-1984 22-09-1982 01-10-1982 03-02-1986